

DATA SHEET



Product: KIT BASE + RESICEM

Ref.: KB + RC

DESCRIPTION

It is a high performance eco cement made from mineral fillers, selected recycled aggregates, obtaining a cement base or level coating for unevenness below 1mm.

USES


Achieve a continuous coating without joints, both for horizontal and vertical surfaces in indoor and outdoor areas. Thanks to its high adherence it is applicable on any material (cement, plaster, plasterboard, tiles, marble or wood) in bathrooms, residences, hotels, shops and leisure premises, and even furniture. Ideal for both new works and renovations without removing the existing surface. Available in different finishes and application techniques, with a range of 120 combinable colours to create thousands of colours. It allows the creation of designs with shapes, prints and logos.

PREPARATION

- Surface must be completely clean, dry, dust-free, with no loose or broken parts; with a humidity level below 3%.
- Preparation of bicomponent Kit (A + B, 1:1 ratio) must be mixed with mixer on low speed until homogeneously combined.
- This Kit is for thin layer levelling of 1 mm. In case of ceramic or porous / irregular surfaces, a levelling or mortar base should be previously applied.

ADVANTAGES

- Quick drying and easy maintenance.
- Apt for execution of continuous works
- High resistance
- Solvent free
- Applicable on existing surfaces
- Combinable with different materials
- Does not require joints
- Stain resistant

YIELD x KIT (KB24+RC8)		KIT FORMATS				KIT PRESENTATION	
m ² per layer		BASE (Component A)		RESICEM (Component B)			
Surfaces	approx. m ²	Ref.	Format	Ref.	Format		
Plasterboard, MDF, Gypsum	34 m ²	KB3	3 kg. Base	RC1	1l.		
Mortar	32 m ²	KB6	6 kg. Base	RC2	2l.		
Base Baseflex	30 m ²	KB12	12 kg. Base	RC4	4l.		
Base Ground	28 m ²	KB24	24 kg. Base	RC8	8l.		

TECHNICAL SPECIFICATIONS (internal quality tests)

TECHNICAL SPECIFICATIONS (interim quality tests)					
	BASE	RESICEM	Density of the mixture: 1.890 kg/l		
Appearance:	Powder	Liquid	mixture pH: 8-9		
Colour:	White	White	Usage time of the mixture: 1-2 h at 20°C 60% relative humidity		
Density (kg/l):	1.440	1.02	Temperature of application: Minimum 5°C and maximum 35°C		
Mixing ratio :	3 parts	1 part	Waiting time before sealing: 12-24 h at 20°C 60% relative humidity		
Dangerous material: Kit NOT classified as ADR/RID, IMDG, ICAO/IATA			Accessibility once sealed: 48 h at 20°C 60% relative humidity		
Drying time between layers: 3-4 h at 20°C 60% relative humidity			Suitable for underfloor heating: Yes (minimum 4cm slabs.)		
Expiration: 1 year from the production date on its packaging			Storage: Minimum temperature of 0°C and max of 40°C		
Compressive strength:			Flexural strength:		
1 day	7 days	28 days	1 day	7 days	28 days
14 N/mm²	23 N/mm²	31 N/mm²	5 N/mm²	9 N/mm²	11.5 N/mm²

TECHNICAL TEST KIT(A+B) (tested product: PU finish)

UNE-EN 13813:2003		
Bond strength, UNE-EN 13892-8:2003	Ceramic surface	1.7 N/mm2 (break support)
	Fibrocement Surface	1.3 N/mm2 (break support)
	MDF Surface	0.6 N/mm2 (break support)
Surface hardness, UNE-EN- 13892-6:2003	72 N/mm ²	
Determination of liquid water transmission (permeability), UNE-EN 1062-3:1999	0.01 Kg./m ² h 0.5	
Determination of flexural properties, UNE-EN ISO 178:2003	0.15 KN./mm ²	
Determination of unpolished slip / skid resistance value (USRV). UNE-ENV 12633:2003, Annex A	29	
Impact Resistance, UNE-EN ISO 6272:2004. Drop height at which the first cracks and diameter produced at this stage are observed	>14.7 Nm At 1500mm WITHOUT defects. Crater diameter: 10.1mm.	
Frictional wear, Böhme, UNE-EN 13892-3:2003	11.2cm ³ /50cm ²	
UNE EN 13501-1:2007		
Fire resistance behaviour after application of finish	Bfl – S1	
UNE-ENV 12633:2003		
Slip resistance after application of finish	Rd: CLASS 3 – Value USRV: 47	

Recommendations and technical data shown in this data sheet are based on laboratory tests and our experience in practice.
We waive any liability for consequences resulting from improper use. Date: August 2016 Version: 1.0

