# **DATA SHEET**

cement designe

Product: TURMALINA 1K
Ref.: TRM-1K-20

## **DESCRIPTION**

High performance eco-cement made from mineral filling and selected recycled aggregates, obtaining mineral texture with bright particles suitable for walls and floors for high traffic.

### **USES**

Achieve a continuous coating without joints, both for horizontal and vertical surfaces in indoor and outdoor areas. Thanks to its high adherence it is applicable on any material (cement, plaster, plasterboard, tiles, marble or wood) in bathrooms, residences, hotels, shops and leisure premises, and even furniture. Ideal for both new works and renovations without removing the existing surface. Available in different finishes and application techniques, with a range of 120 combinable colours to create thousands of colours. It allows the creation of designs with shapes, prints and logos.

#### **PREPARATION**

- Surface must be completely clean, dry, and dust-free, with no loose or broken parts; with a humidity level below 3%.
- -The powder component must be mixed with water on low revolution until a homogeneous mixture. In case of color use, incorporate the complete desired pigment into the mixture and then mix it until a fully diluted and homogeneous mass.
- This product is a final finish. In case of ceramics or porous / irregular supports, a regularization base or mortar must be applied previously.

#### **ADVANTAGES**

- Quick drying and easy maintenance
- Suitable for execution of continuous works
- High resistance
- Solvent free

- Applicable on existing surfaces
- Combinable with different materials
- Does not require joints
- Stain resistant

YIELD x ud (ZR-1K-20)		KIT FORMATS			PRESENTATI	PRESENTATION KIT	
Layer per m2		ZIRCONIO (C	Comp. A)	WATER (Comp. B)	W	1000	
Surface	m² aprox.	Ref.	Format		A /	Sec. and	
Fine texture	25 m <sup>2</sup>	TRM-1K-10	10 kg.Turmalina	3 L	Polvo	Agua	
Medium texture	20 m <sup>2</sup>	TRM-1K-20	20 kg.Turmalina	6 L	Powder	Water	
Thick texture	17 m <sup>2</sup>				The state of the s	The state of the s	

ESPECIFICACIONES TÉCNICAS (ensayos de calidad internos)								
	DIAMANTE	WATER	Density of the mix	<b>ture:</b> 1,950 kg/l				
Appearance:	Powder	Líquid	Mixture pH: 9					
Color:	white	colourless	Usage time of the	Usage time of the mixture: 1-2 h at 20°C   60% relative humidity				
Density (kg/l):	1,400	1,00	Temperature of application:: Minimum 5°C and maximum 35°C					
Mixing ratio :	3 volumes	1 volume	Waiting time before sealing: 12-24 h. to 20°C   60% relative humidity					
Dangerous material: NOT classified as ADR/RID, IMDG, ICAO/IATA			Accessibility once	Accessibility once sealed: 48 h. to 20°C   60% relative humidity				
<b>Drying time between layers:</b> 3-4 h. to 20°C   60% relative humidity			Suitable for under	Suitable for underfloor heating: Yes (minimum 4cm slabs.)				
<b>Expiration:</b> 1 year from the production date on its packaging			Storage: Minimum	Storage: Minimum temperature of 0°C and max of 40°C				
Compressive strength:			Flexural strength::	Flexural strength::				
1 day	7 days	28 days	1 day	7 days	28 days			
12 N/mm <sup>2</sup>	20 N/mm <sup>2</sup>	29 N/mm <sup>2</sup>	5 N/mm <sup>2</sup>	8 N/mm <sup>2</sup>	11 N/mm <sup>2</sup>			

KIT TECHNICAL TEST (A+B) (tested product: PU finish) UNE-EN 13813:2003			
Bond strength,	Ceramic surface	1,7 N/mm² (break support)	
UNE-EN 13892-8:2003	Fibrocement Surface	1,3 N/mm <sup>2</sup> (break support)	
	MDF Surface	0,6 N/mm <sup>2</sup> (break support)	
Surface hardness, UNE-EN- 13892-6:2003	72 N/mm <sup>2</sup>		
Determination of liquid water transmission (permeability), UNE-EN 1062-	0,01 Kg./ m <sup>2</sup> h 0,5		
3:1999			
Determination of flexural properties, UNE-EN ISO 178:2003	0,15 KN./mm <sup>2</sup>		
Determination of unpolished slip / skid resistance value	29		
(USRV). UNE-ENV 12633:2003, Annex A			
Impact Resistance, UNE-EN ISO 6272:2004. Drop height at which the first	>14,7 Nm		
cracks and diameter produced at this stage are observed	At 1500 mm WITHOUT defects. Crater diameter: 10,1 mm.		
Frictional wear, Böhme, UNE-EN 13892-3:2003	11,2 cm <sup>3</sup> / 50 cm <sup>2</sup>		
UNE EN 13501-1:2007			
Fire resistance behaviour after application of finish	Bfl - S1		
UNE-ENV 12633:2003			
Slip resistance after application of finish	Rd: CLASS 3 – Value USRV: 47		

Recommendations and technical data shown in this data sheet are based on laboratory tests and our experience in practice. We waive any liability for consequences resulting from improper use. Date: August 2016 Version: 1.0





